



NIZHNEKAMSKNEFTEKHIM USA

92 Front Street – Hempstead, New York 11550

Phone: 516-542-0500

Fax: 516-542-0055

www.www.nizhusa.com

CHLORINATED BUTYL RUBBER - CBK-150

CAS Number: 68081-82-3 Design specification: TU 2294-096-05766801-2000

This is a product of butyl rubber chlorination with unsaturation of not less than 1.8 % mol. Chlorobutyl rubber is designed for use in the tire and rubber production industry for the manufacture of medical and general purpose articles.

Item	Specification	Test Method
Mooney viscosity MB 1+8 (125° C)	45 - 55	Para graph 4.2 of TU, or ASTM D 1646
Chlorine mass content percent	1.15 – 1.35	Para graph 4.3 of TU, or ASTM E 442
Ash content – not more than – percent	0.50	Para graph 4.4 of TU, or ISO 247 or ASTM D 5667
Antioxident “Irganox 1010”, mass content, percent	0.05	Paragraph 4.5 of TU
Loss of mass at drying, percent maximum	0.50	Para graph 4.7 of TU, or ISO 248 or ASTM D 5668
Modulus at 300% elongation, MPa, minimum	4	Para graph 4.10 of TU, or ISO 37 or ASTM D 412
Tensile Strength, MPa, minimum	13	Paragraph 4.10 of TU or ISO 37 or ASTM D 412
Ultimate elongation, percent minimum	400	Paragraph 4.10 of TU or ISO 37 or ASTM D 412

Supply Form: 30 (plus/minus 1) kilo bales

Packaging: Polyethylene film, wooden and metal pallet boxes

Storage: Rubber in pallet boxes should be stacked maximum three tiers high. Storage in warehouses, away from direct sun and precipitation and contamination at temperature not higher than 30° C (86° F).

Information contained in this document is provided to the best of our knowledge and is considered true as per revision date. This specification does not release the customer from obligation to check the product as to its suitability for the intended area of usage. We do not accept any liability for loss and/or damage which may occur as a result of the use of this information.

Revised: December 3, 2003