



NIZHNEKAMSKNEFTEKHIM USA

92 Front Street – Hempstead, New York 11550

Phone: 516-542-0500

Fax: 516-542-0055

www.www.nizhusa.com

## POLYBUTADIENE RUBBER SKD

Synthetic solution cis-butadiene rubber (Nd) is a product of solution polymerization of butadiene using neodim compounds as a catalyst. The 1.4 cis content in the rubber is 97% minimum. This rubber is intended for use in tires, technical-rubber and other branches of industry.

### Main Quality Characteristics

	<u>Group 1</u>	<u>Group 2</u>	<u>Group 3</u>	<u>Test</u> <u>GOST</u>
* Mooney viscosity ML, 1+4 (100°C)	40-49	50-59	60-70	10722
* Viscosity spread within a batch, max.	5	5	5	
* Loss of mass at drying, %, max.	0.5	0.5	0.5	19338
* Ash content, %, max.	0.5	0.5	0.5	19816.4
* Antioxidant (agidol-2) content: %, max.	0.6-1.0	0.6-1.0	0.6-1.0	19920.12

#### Packaging:

30-kilo bales wrapped with high quality polyethylene film (per GOST 10354) are placed in wooden pallet-boxes each weighing 450 kilos net. 15 bales per box.